

TWISTED PAIR CABLE WITH DUAL LAYER INSULATION HAVING
IMPROVED TRANSMISSION CHARACTERISTICS

Field of the invention

5

The present invention relates to twisted pair cables which can be used in high frequency applications.

PRIOR ART

Description of the prior art

10

Twisted pair cables have become the physical media of choice for local area networks in the last 10 years. The current EIA/TIA 568 A Category 5 specifications (and the associated addenda) for these cables call for performance up to a frequency of 100 MHz.

15

Installed transmission systems were, until recently, operating only at 10 Mbit/s and did not use all the available bandwidth offered by cables meeting the existing specifications. In fact, the Ethernet protocol used in over 70% of the installed networks, employs only two pairs of the available four and uses half-duplex transmission, i.e. one pair is transmitting while the other is receiving.

20

In the last five years, new transmission technology, operating at 100 Mbit/s has been rapidly expanding in the marketplace. At the same time, improved cables with transmission characteristics exceeding the current EIA/TIA 568 A Category 5 specifications (and the associated addenda) were also developed. Despite the assurance of performance promised by the existing specifications, cable manufacturers have developed cables with improved performance as an insurance policy for future applications. In addition, process variation during the manufacture of the cable and further handling during installation were causing deterioration in cable performance, thus the requirement of transmission characteristics that exceeded the current specifications.

25

More recently, new data transmission technology has indeed pushed the speed limit to 1 Gigabit/s and higher. This transmission technology and some of the existing 100 Mbit/s transmission technologies, when applied to twisted pair

30

4/14/13

OFFICE 2050560

disposed around it is difficult to achieve and slows down the manufacturing processes. In addition, the cable diameter is increased by at least 20%. The overall cost of the cable is also substantially increased due to the additional cost of the center member and higher jacketing material costs.

5

INVENTION
Summary of the invention

It is the object of this invention to eliminate many of the difficulties inherent in the cables of the prior art while substantially reducing both cross-talk impairments and impedance irregularities in a cost competitive manner respectful of the EIA/TIA specifications.

10

In accordance with the invention, this object is achieved with a twisted pair cable comprising a plurality of pairs, each of said pairs comprising two conductors, each of said conductors is covered with an inner layer insulator and an outer layer insulator, said conductors being eccentric with respect to the overall insulation of said inner and outer layer insulator.

15

The present invention also concerns a method for making the same.

D D
Brief description of the drawings

20

The present invention and its advantages will be more easily understood after reading the following non-restrictive description of preferred embodiments thereof, made with reference to the following drawings in which:

25

Figure 1 is a cross-sectional representation of a conductor of a twisted pair cable according to a preferred embodiment of the present invention;

Figure 2a is a cross-sectional representation of a conductor of a twisted pair cable according to another preferred embodiment of the present invention;

Figure 2b is a cross-sectional representation of a conductor of a twisted pair cable according to yet another preferred embodiment of the present invention;

30

Figure 3 is a schematic representation of the stretching and the twisting of two conductors to form twisted pair cable according to a preferred embodiment of the present invention;

Figure 4a is a schematic representation of the eccentricity of the conductors with respect to the insulation according to a preferred embodiment of the present invention; and

Figure 4b is a schematic representation of a twisted pair cable according to the prior art.

Description of a preferred embodiment of the invention

As mentioned above, the present invention concerns a cable which eliminates many of the difficulties inherent in the cables of the prior art while substantially reducing both cross-talk impairments and impedance irregularities in a cost competitive manner respectful of the EIA/TIA specifications discussed above.

In accordance with a broad aspect of the invention, the cable of the present invention comprises a plurality of pairs. Each pair comprises two conductors 11, each conductor comprising an inner layer insulator 13 and an outer layer insulator 15. The conductors 11 are eccentric with respect to the overall insulation dimension, as clearly shown in Fig. 4a. Consequently, referring now to Fig. 4a, the conductors 11 are separated by a distance S1 which is smaller than the separators S2 of conductors 11 in adjacent pairs. Stated another way, the conductors 11 are asymmetric, such that the conductors 11 are closer to each other in a pair than to conductors 11 in adjacent pairs in contact at the outer surface opposite the conductors 11.

In a preferred aspect of the invention, each conductor 11 is provided with an inner layer insulator 13, and an outer layer insulation 15. Preferably, one of the layers has a first modulus of elasticity, and the other layer has a second modulus of elasticity, where the first modulus is greater than the second modulus. Consequently, in order to obtain the cable of the present invention, a twisted pair cable is provided comprising of conductors insulated with a thick inner layer and a thinner outer layer (see Fig. 1). The inner dielectric layer 13 can be chosen from a group of extrudable polymers that have a modulus of elasticity exceeding 64 Kpsi at room temperature, a dielectric constant lower than 2.5 and a loss factor lower

than 0.0003 when tested from 1 MHz to 1 GHz. The outer dielectric layer 15 is chosen from another group of extrudable polymers, also called thermoplastic elastomers, that have a modulus of elasticity below 35 Kpsi at room temperature and similar but not necessarily better electrical characteristics. (See Fig 1)

5 In another embodiment of this disclosure, a thinner inner dielectric layer 13 is chosen from the group of elastomers, while the relatively high elastic modulus polymers are applied as a thicker outer layer 15. (See Fig 2a)

10 In a third embodiment of this disclosure, a inner dielectric 13 is chosen from the group of elastomers the relatively high elastic modulus polymers is applied as an intermediary layer 15 and an outer layer 17 is chosen from the same group of extrudable elastomers, as the inner dielectric 13. (See Fig 2b)

15 One major mechanical characteristics of elastomers is their capacity to undergo relatively high strain in the elastic domain under relatively low mechanical stress and achieve complete recovery following the release of the stress. Conversely, for high modulus materials, there is a small strain domain where the material behaves elastically under relatively high stress; beyond that domain, the high modulus materials deform permanently or plastically.

20 The present invention takes advantage of the presence of an elastomer as the outer or the inner layer of the insulated conductor, and possibly in both outer and inner layer of a three layered insulation, to create, during the process of pair twisting and pair assembly, a structure that is mechanically pre-stressed and will resist further deformations. The resulting cable will have reduced cross-talk impairments and impedance irregularities and will maintain its characteristics following packaging and installation.

25 During the twisting action, when the individual insulated conductors come into contact, the elastomer outer layer is constrained into the high modulus inner layer following the overall ductile deformation of the copper conductors. As better shown in Fig. 3, the conductors 11 provided with the insulations are subjected to longitudinal forces **F11** and **F21**, and lateral forces **F12** and **F22** at the twisting apparatus pay-offs.

30

While the perpendicular tensions **F12**, **F22** resultant during the process are too small to effect a significant elastic deformation of the high modulus layer, the

elastomer layer can be readily deformed to effect a permanent deformation that is still in the elastic domain following the twisting process. Thus, the twisted pair constructed as described above constitutes, within given boundaries of flexing of the twisting strand, a mechanically pre-stressed structure and will resist further deformations.

It was found that, in order to obtain the advantages disclosed in the present application, the outer or the inner thin elastomer layer thickness is preferably at least 15% of the overall insulation thickness. This is also the case when the twisted pair cable includes an inner and the outer elastomer layer and a middle extrudable polymer layer. Consequently, the combined thickness of the inner and outer elastomer layers is preferably at least 15% of overall insulation thickness. The intensity of the forces F_{11} , F_{12} , F_{21} , F_{22} in play on the individual conductors and the twisted pair during the manufacturing process are also important in obtaining the disclosed advantages. It should be noted that the series of forces F_{11} and F_{21} is equivalent to the resulting force F_0 .

The structure of the resulting twisted pair, as disclosed above, is asymmetric i.e.: the separation S_1 between the two conductors in a pair is smaller than the separation S_2 between the two conductors of an adjacent pair (Fig. 4a). In the known art, twisted pairs of perfectly centred insulated conductors have a symmetrical structure whereby the separation S_1 between the two conductors in a pair is equal to the separation S_2 between the two conductors of an adjacent pair (Fig. 4b).

INS A2 > P > The immediate advantage of such a pair structure is that, while the impedance of the proposed cable is equivalent to a cable of identical conductor separation, the separation between the pairs of the proposed cable exceed the norm in a cable with symmetrical pair structure. The higher separation between pairs induces tangible electrical performance improvements that result in a cable with reduced cross-talk impairments and lower signal attenuation. Both reductions contribute to a much improved signal to noise performance of the resulting cable. For example, an experimental cable with a 0.008" overall insulation thickness having a 0.003" outer elastomer layer and a 0.036" overall diameter has shown an improvement of at least 35% in the near end cross-talk (normal scale) when

compared with a standard cable of same construction in a frequency range from 1 to 300 MHz.

5 The inherent advantages of the proposed cable are not limited to the improvement of the final cable cross-talk and attenuation characteristics. The presence of an elastomer layer in the insulated conductor constitutes a definite advantage during the subsequent processing stages of the cable. During the insulation process, the elastomer layer will cushion the unavoidable variations in tension generated during the spooling of the insulated conductor into the take-up reels. In addition, better spooling of the insulated conductor is obtained on the take-up reels. Subsequently, the twisting process is helped by the better spooling that will lower the variation in pay-off speeds between the two individual insulated conductors of the pair. More importantly, the unavoidable variations in tension, caused by speed differences and irregularities in the mechanical devices during the twisting, are absorbed by the elastomer layers and limit the dimensional variations to the thickness of an elastomer layer. Consequently, the proposed cable has very stable input impedance as a function of the frequency from 0.772 to 350 MHz due to the limitation in the possible variation of the separation between the conductors S_1 that is limited to the elastomer layer thickness. This variation does not exceed 0.0002". Prior art (US patent no. 5,606,151) has shown that such a variation will result in a 6 ohms impedance variation, well below the maximum +/- 15 ohms specified by the EIA/TIA specifications. The impedance stability is also reflected in the fact that the return loss of the proposed cable is very low without any backtwisting of the insulated conductors. Experimental results have shown, in fact, that there is little discernible difference between backtwisted insulated conductors and non-backtwisted ones.

25 It was also shown that by varying the twisting tension, one can obtain the same results as above with thinner elastomer layers. This unexpected property can provide the designer with the ability to develop a cable with perfectly balanced impedance properties without varying the overall diameter of the insulated conductor.

30 Unexpectedly, the proposed cable has also very low delay skew i.e. the difference between the propagation speed in the four pairs is minimal, well below

the required by the same C1 draft. This characteristic is reflected in the fact that the pairs signal attenuation curves are almost identical. As mentioned in the background of the invention, a low delay skew is essential for the operation of bi-directional transmission protocols.

5 The overall transmission characteristics of the proposed cable are within the requirements of the latest draft C1 of the proposed Category 6 addendum to the TIA/EIA 568 A.

10 The elastomer layer can also be used as a carrier for colour and flame retardant additives (but only when the elastomer layer is the outer layer). By doing so, an additional improvement in the electrical performance of the cable will be obtained at a lower cost in additives that otherwise are dispersed in the entire insulation. In a preferred embodiment, the inner layer elastomer will incorporate particles of inorganic flame retardants or other flame retardant polymer having excellent dielectric capabilities and the outer layer will be a flame retardant polymer with low dielectric constant and loss factor.

15 In addition, the elastomer layer can be foamed in order to reduce the signal attenuation of the individual pair and of the resulting 4 pair cable. Foaming will also increase the compressibility of elastomer layer, thus increasing the asymmetry of the twisted pairs. It was disclosed above that this feature of the present disclosure contributes to the reduction in cross-talk impairments.

20 An additional embodiment of the disclosure is a foam-skin insulated conductor that is composed of a first foamed layer and a second elastomer layer with a very low elastic - 15 Kpsi and lower - modulus. The mechanical fragility of traditional foam-skin insulation designs is well known. In the proposed design, the elastomer skin layer acts as a cushion that mechanically protects the fragile foam layer during the subsequent process stages.

25 The use of the above asymmetrical pair design in the STP (Shielded Twisted Pair) and ScTP (screened twisted pair) cable is an additional advantageous application of the concept. An asymmetric pair surrounded by a metallic shielded film will have lower attenuation, and better impedance stability that a standard pair structure. In recent STP cable designs, foam is the

30

recommended insulation. Thus, the elastomer top layer will be helpful in protecting the foamed layer as disclosed above.

Another potential application of the asymmetric pair concept is in the area of multi-pair outside plant cables. The widespread penetration of the Internet has raised the bandwidth requirements of the existing telephone network. Solutions for the trunk section of the network are available in the form of the fibre and or fibre/coax technology. The distribution to single residences and small offices is more problematic given the enormous cost involved in the complete conversion to fibre. Upgrading the capability of outside plant copper based drop wires is a very attractive cost effective solution. Drop wires incorporating the asymmetric pair concept will considerably increase the bandwidth of the resulting multi-pair outside plant cables, especially the ones incorporating a metallic screen.

It should be understood that one important aspect of the invention is the use of two different insulator layers, one of which can undergo a permanent deformation under predetermined conditions, while the other layer does not undergo a permanent deformation. Although preferred materials have been described herein, it should be apparent to a person skilled in the art that other materials can be used and which will meet the object of the invention.

Although the present invention has been explained hereinabove by way of a preferred embodiment thereof, it should be pointed out that any modifications to this preferred embodiment within the scope of the appended claims is not deemed to alter or change the nature and scope of the present invention.